



G F
3 COLLECTION
GROOVE FLASHES

GF3.01

GROOVE FLASHES



GF3.01.1 350 ϕ cm



GF3.01.2 350 ϕ cm



GF3.01.3 350 ϕ cm



technical
specifications.

BROADLOOM PA SAXONY 2800

| Identification | Standard | Product Data |
|------------------------------|-------------------------|--------------------------------------------------------------------------------------------------------|
| Manufacturing process | DIN ISO 2424 | Tufting 1/10" |
| Frontside structure | DIN ISO 2424 | Cut pile / Saxony |
| Color | DIN ISO 2424 | Chromojet Print |
| Pile material | | 100% Polyamid PA |
| Primary backing | DIN ISO 2424 | PP Woven |
| Secondary backing | DIN ISO 2424 | Felt backing |
| Pile weighth | DIN ISO 2424 | Approx. 1050 g/m ² |
| Total weight | ISO 8543 | Approx. 2800 g/m ² |
| Pile height | ISO 1766 | Approx. 5.5 mm |
| Total thickness | ISO 1765 | Approx. 10,00 mm |
| Number of knots | ISO 1763 | Approx. 213.300 /m ² |
| Width | DIN 3018 | Approx. 400 cm |
| Wear classification | EN 1307:2004 | 33 heavy contract |
| Comfort rating | EN 1307:2004 | LC 4 |
| Surface resistance | ISO 10965 | Approx. Ω |
| Vertical resistance | ISO 10965 | Approx. Ω |
| Sound absorption coefficient | ISO 11654:1997-07 | Hz 125 250 500 1000 2000 4000 α _p 0,02 0,06 0,10 0,22 0,39 0,44 α _w 0,20Hz |
| Impact sound insulation | EN ISO 10140:2010 | Approx. 33dB |
| Antistatic behavior | ISO 6356:2012 | < 2 kV |
| Thermal resistance | ISO 8302:1991 | Approx: 0.11K*m/ W _w |
| Fire rating | DIN EN 13501-1 | B _{fl} - s1 |
| Color fastness to light | ISO 105-B02:2000 | 5-6 |
| Color fastness to water | DIN EN ISO 105 E01:2013 | 5 |
| Rubbering fastness dry/wet | DIN EN ISO 105 X12:2002 | 5 |

PA SAXONY 2900

| Identification | Standard | Product Data |
|------------------------------|-------------------------|--------------------------------------------------------------------------------------------------------|
| Manufacturing process | DIN ISO 2424 | Tufting 1/10" |
| Frontside structure | DIN ISO 2424 | Cut pile / Saxony |
| Color | DIN ISO 2424 | Chromojet Print |
| Pile material | | 100% Polyamid PA |
| Primary backing | DIN ISO 2424 | PP Woven |
| Secondary backing | DIN ISO 2424 | Felt backing |
| Pile weighth | DIN ISO 2424 | Approx. 1245 g/m ² |
| Total weight | ISO 8543 | Approx. 2900 g/m ² |
| Pile height | ISO 1766 | Approx. 6 mm |
| Total thickness | ISO 1765 | Approx. 10,50 mm |
| Number of knots | ISO 1763 | Approx. 237.000 /m ² |
| Width | DIN 3018 | Approx. 400 cm |
| Wear classification | EN 1307:2004 | 33 heavy contract |
| Comfort rating | EN 1307:2004 | LC 4 |
| Surface resistance | ISO 10965 | Approx. Ω |
| Vertical resistance | ISO 10965 | Approx. Ω |
| Sound absorption coefficient | ISO 11654:1997-07 | Hz 125 250 500 1000 2000 4000 α _p 0,01 0,05 0,11 0,28 0,37 0,48 α _w 0,30Hz |
| Impact sound insulation | EN ISO 10140:2010 | Approx. 35dB |
| Antistatic behavior | ISO 6356:2012 | < 2 kV |
| Thermal resistance | ISO 8302:1991 | Approx: 0.13K*m/ W _w |
| Fire rating | DIN EN 13501-1 | B _{fl} - s1 |
| Color fastness to light | ISO 105-B02:2000 | 5-6 |
| Color fastness to water | DIN EN ISO 105 E01:2013 | 5 |
| Rubbering fastness dry/wet | DIN EN ISO 105 X12:2002 | 5 |



PA SAXONY 3230

| Identification | Standard | Product Data |
|-----------------------|------------------------|-----------------------------------|
| Manufacturing process | DIN ISO 2424 | Tufting 1/10" |
| Frontside structure | DIN ISO 2424 | Cut pile / Saxony |
| Color | DIN ISO 2424 | Chromojet Print |
| Pile material | | 100% Polyamid PA 6.6 |
| Primary backing | DIN ISO 2424 | PP Woven |
| Secondary backing | DIN ISO 2424 | Felt backing 500 g/m ² |
| Pile weight | DIN ISO 2424 | +/- 1600 g/m ² |
| Total weight | ISO 8543 | +/- 3230 g/m ² |
| Pile height | ISO 1766 | +/- 10 mm |
| Total thickness | ISO 1765 | +/- 12.5 mm |
| Number of knots | ISO 1763 | +/- 1193000 /m ² |
| Width | DIN 3018 | +/- 400 cm |
| Wear classification | EN 1307:2004 | 32 heavy contract |
| Comfort rating | EN 1307:2004 | LC 5 |
| Fire rating | DIN EN 13501-1 | C _{fl} -s1 |
| Remarks | Only suitable for rugs | |



These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to alter specifications without notice. Due to method of manufacture, perfect pattern and/ or colour matching cannot be guaranteed. In cut pile carpet, shading/ pile reversal might occur without affecting overall quality and suitability. Shading/ pile reversal will not be considered as a manufacturing fault and will not affect durability of the carpet.